

Chemical Compatibility with Other Building Materials and Sealants

Frequently during the design of an assembly, the designer will question the chemical compatibility of self-adhered flexible flashings with other materials. VYCOR® Self-Adhered Flashings (VYCOR® Plus, VYCOR® V40, VYCOR® Aluminum, VYCOR® PRO, and VYCOR® Deck Protector) are chemically compatible with most substances and products that are normally present in common application environments. VYCOR® Self-Adhered Flashings are compatible with acids, bases and salts.

Generally, there is no chemical compatibility issue if a material contacts the film surface of the self-adhered flashing. If the contact area is the adhesive component of the flashing, there is need to investigate further. As a general rule, the material must be sound, functional and firmly bonded to the substrate.

The design of the connection between the two materials will vary depending on the composition of the material. Some of the more common materials are detailed below.

Building Materials

VYCOR® Self-Adhered Flashings are applied directly to exterior sheathing panels such as plywood (including fire-treated plywood), oriented strand board (OSB), exterior gypsum board, glass mat surfaced gypsum board, and extruded polystyrene. VYCOR® flashings are compatible with chromated copper arsenate (CCA), alkaline copper quaternary (ACQ), ammoniacal copper zinc arsenate (ACZA), pressure-treated woods and pressure-treated plywoods.

Windows & Doors

The rubberized asphalt of VYCOR® Plus, VYCOR® V40, VYCOR® Aluminum, and VYCOR® Deck Protector is compatible with rigid polyvinyl chloride (PVC), but not plasticized polyvinyl chloride. VYCOR® PRO is compatible with rigid and plasticized PVC nailing flanges. Some arched/round shape windows may use a plasticized PVC nailing flange. Consult with the window manufacturer to determine if the nailing flange is constructed of plasticized PVC.

For further details refer to Technical Letter 6, *Chemical Compatibility with Vinyl Windows*.

Note: Per ASTM E2112, "The application of sealant to the exterior face of the (window) flange is not necessary if using self-adhesive type flashing over the mounting flange."

Weather Resistive Barriers

Vycor® Self-Adhered Flashings are applied to the structural substrate. They should be integrated with the weather resistive barrier to form water-shedding laps.

VYCOR® Self-Adhered Flashings are compatible with the following weather resistive barriers:

- VYCOR® enV®-S™
- VYCOR® enV® (cured liquid)
- Spun-Bonded Polypropylene
- Spun-Bonded Polyethylene
- Red Rosin Paper
- Asphalt Saturated Felt
- Spun-Bonded Polyethylene
- Red Rosin Paper
- Asphalt Saturated Felt
- Polyurethane Coatings
- Polyethylene Sheet/Visqueen
- Asphaltic Dampproofing

- Perm-A-Barrier® Systems
- OSB Panels with integrated WRB coatings (such as Huber Zip System® panels)

Sealant and Caulking Materials

Most sealants are chemically compatible with VYCOR® Self-Adhered Flashings provided that the sealant is applied to the high-density polyethylene film component of the flashings. There are various sealant formulations on the market that may or may not be compatible with the adhesive layer of VYCOR® Self-Adhered Flashings. For further details, refer to Technical Letter 7, *Chemical Compatibility Between VYCOR® Self-Adhered Flashings and Sealants*.

Non-Compatible Materials

VYCOR® Self-Adhered Flashings are not compatible with the following substances:

- Creosote
- Pentachlorophenol
- Polysulfides
- Diesel Fuel
- Gasoline/Oil
- Hydrocarbon Solvents
- EPDM*
- Plasticized PVC*
- TPO*
- Uncured Neoprene
- High concentrations of pitch
(resin from soft wood)

* VYCOR® PRO is compatible with plasticized PVC window flanges, EPDM and TPO. VYCOR® PRO is intended for non-roof applications only.

Primers

Only GCP approved primers should be used with VYCOR® Self-Adhered Flashings. VYCOR® Plus, VYCOR® V40, VYCOR® Aluminum, VYCOR® PRO and VYCOR® Deck Protector are compatible with the following GCP primers:

- PERM-A-BARRIER® WB Primer
- BITUTHENE® Primer B2 LVC
- PERM-A-BARRIER® Primer Plus

gcpat.com | North America Customer Service: 1-866-333-3726

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

VYCOR, VYCOR enV, PERM-A-BARRIER and BITUTHENE are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140 USA.

In Canada, GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

Printed in U.S.A. TP-060-0416 RE0067 CD/PDF

