

TYTRO[®] HC 250

Air-entraining admixture for shotcrete

Product Description

TYTRO[®]AE 250 is an air-entraining admixture which generates a highly stable air-void system for increased protection against damage from freezing and thawing, severe weathering, or de-icer chemicals. TYTRO[®]AE 250 is a complex mixture of organic acid salts in an aqueous solution specifically formulated for use as an air-entraining admixture for shotcrete and is manufactured under rigid control which provides uniform, predictable performance. TYTRO[®]AE 250 is supplied ready-to-use and does not require pre-mixing with water.

By agitation of concrete mixers, TYTRO[®]AE 250 disperses and generates millions of discrete semi microscopic bubbles throughout the concrete composite. Once thoroughly mixed, the shotcrete contains a stable network of bubbles which act much like ball bearings increasing mobility, or plasticity, of the mix.

TYTRO[®]AE 250 complies with ASTM C1141 Type II Grade 8 Standard Specification for Air-Entraining Admixtures for Shotcrete and ASTM C260 Standard Specifications for Air-Entraining Admixtures for Concrete.

Product Advantages

- Increased durability to all exposures
- Improved workability
- Reduced water content – with no loss of slump
- Improved pumpability through high initial air content
- Improved placement
- Bleeding and segregation minimized

Uses

TYTRO[®]AE 250 is used in all shotcrete applications to improve air entrainment stability and durability, especially in the following applications:

- Temporary and permanent rock support in tunnels
- Underground rock support in mining
- Slope stabilization

TYTRO[®]AE 250 introduces a high amount of uniformly dispersed stable small air bubbles in all shotcrete applications which are desired for providing high initial air content to achieve superior pumpability characteristics.

Storage

Temperature

TYTRO®AE 250 should be stored at a temperature range of 2 °C to 35 °C.

If TYTRO®AE 250 freezes, it will return to full effectiveness after thawing and thorough mechanical agitation. It is recommended that your local GCP sales representative be consulted prior to the use of any products that may have been frozen. Performance tests should always be carried out prior to use.

Conditions

TYTRO®AE 250 must be kept in closed plastic containers or closed tanks.

Shelf Life

If stored in tightly closed original containers and under the above mentioned conditions, TYTRO®AE 250 has a shelf life of at least 12 months. Please contact your local GCP sales representative regarding the suitability for use if the shelf life of TYTRO®AE 250 has been exceeded.

Addition Rates

The dosage of TYTRO®AE 250 can vary based on the mix design, type and content of cementitious materials, water-to-cementitious materials ratio, concrete temperature, ambient temperature and required air for exposure conditions.

Entrained air results in increased yields with a consequent decrease in the cementitious materials content of the placed shotcrete. This condition calls for a mix adjustment, usually accomplished by reducing the fine aggregate content. This is in addition to the reduction in water content brought about by the increase in plasticity.

The dosage of TYTRO®AE 250 normally ranges between 30 and 320 mL per 100 kg of cement. GCP recommends that trials be performed with cement and aggregates under local conditions before use to assess and optimize dosage rates and performance.

Mixing & Dispensing

In general, it is recommended that TYTRO®AE 250 be added to the mix near the beginning of the batch sequence for optimum performance.

It is recommended that TYTRO®AE 250 be introduced into the mixer by means of automatic dispensing equipment. A range of equipment is available, and advice on supply and fitting is available from GCP on request.

Packaging

TYTRO[®]AE 250 is available in bulk and in drums.

Health and Safety

Avoid eye and skin contact and wear rubber gloves and safety glasses when handling this product. If contact occurs, rinse with plenty of water and seek medical advice.

For further information, refer to the SDS (Safety Data Sheet) or contact your local GCP representative.

Compatibility

TYTRO[®]AE 250 is compatible with all GCP TYTRO[®]shotcrete admixtures.

Pretesting of the shotcrete mix should be performed before use and as conditions and materials change in order to ensure compatibility with other admixtures.

For use with other shotcrete admixtures systems, we recommend you contact GCP for further advice.

Properties

Form	Liquid
Color	Brown
Density (g/cm ³)	1.04 ± 0.02

gcpat.com | North America customer service: 1-877-423-6491

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

TYTRO is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140 USA.

In Canada, 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

Ce document est à jour seulement à la date de la dernière mise à jour indiquée ci-dessous et n'est valide que pour une utilisation au Canada. Il est important que vous consultiez toujours les informations actuellement disponibles sur l'URL ci-dessous pour fournir les informations les plus récentes sur le produit au moment de l'utilisation. Des documents supplémentaires tels que les manuels de l'entrepreneur, les bulletins techniques, les dessins détaillés et les recommandations détaillées ainsi que d'autres documents pertinents sont également disponibles sur www.ca.gcpat.com. Les informations trouvées sur d'autres sites Web ne doivent pas être utilisées, car elles peuvent ne pas être à jour ou applicables aux conditions de votre site et nous déclinons toute responsabilité quant à leur contenu. S'il y a des conflits ou si vous avez besoin de plus d'informations, veuillez contacter le service client de GCP.

Last Updated: 2018-12-12

ca.gcpat.com/solutions/products/tytro-shotcrete-system/tytro-hc-250