

DE NEEF[®] Rock-Tite B3

Two Component Polyurethane Foam

Product Description

Rock-Tite B-3 is a two component high density polyurethane foam. It contains no CFC's or HFC's to create its cellular structure. Density of the product is formulated for 15-20 lbs. per cubic foot. Pour temperatures remain stable between 120°F - 130°F in 8" lifts.

Product Advantages

- 15-20 lb/ cu.ft foam density
- Stable pours at elevated temperatures
- Very high compressive strength

Product Applications

- Fill rock fissures
- Voids
- Soil stabilization
- Mine tunnels
- Slip-lined pipes

Properties

ROCK-TITE B-3

Viscosity Part A (77°F)	170-230 cps	Brookfield
Viscosity Part B (77°F)	205-230 cps	Brookfield
Mixing ratio by volume	1:1 (A:B)	
Property	Cured	Test (ASTM)
Density	15-20 pcf	D1622
K-Factor	Fresh 0.14 Aged 0.145	C518 C518
Compressive strength	2000 psi (10% deflection) 800 psi (0% deflection)	D1621
Tensile strength	150 psi	D638
Maximum use Temp.	250°F	
Expansion	3-4 V (volumes)	
Dimensional stability (158°F-97% RH) for 2 weeks	< 1%	

Note: The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.

Installation Guidelines

Warning: Consult the Technical Data Sheets and SDS before using.

Installation Instructions: For detailed installation instructions refer to the DeNeef technical bulletin for your application.

Rock-Tite B-3 is designed to be pumped in place using conventional plural component equipment. Thorough mixing is essential for proper cured density. Due to the fast setting characteristics, it is recommended that an impingement type mix system be used.

Injection: During injection the grout will follow the path of least resistance. When the material has stopped penetrating it will continue to expand against the limits of the confined space and compress within itself, forming a dense, closed cell foam.

Extreme conditions: For application procedures in extreme temperatures and specific environments or equipment recommendations call the DeNeef Technical Service Department.

Cleaning: Clean all tools and equipment which have been in contact with the resin with DeNeef Washing Agent before resin has cured. Products should be disposed of according to local, state, and federal laws.

Packaging & Handling

Rock-Tite B-3:

10 gallon (2 x 5 gal. pails)

100 gallon (2 x 50 gal. drums)

Both components should be stored in a dry place at temperatures between 65°F and 80°F. Do not thin with solvents. Confirm product performance in specific chemical environment prior to use. Substrate temperature must be at least 5°F above the dew point.

Health and Safety

Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest. Refer to Safety Data Sheet (SDS) for detailed safety precautions. SDS's can be obtained from GCP Applied Technologies or from our web site at gcpat.com.

For emergencies, call CHEMTREC 1-800-424-9300.

Limitations

Rock-Tite B-3 requires very high shear in order to mix properly and should always be run through an impingement type mixer during pumping. Low temperatures will significantly affect viscosity. If site temperatures are extremely low, heat bands or heated water baths may be used on the pails before and during installation to maintain the product's temperature. Avoid splashing water into open containers, as the material is water activated. Avoid exceeding 90o F when warming.

ca.gcpat.com | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use that would infringe any patent, copyright or other third-party right.

DE NEEF is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies, Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

Ce document est à jour seulement à la date de la dernière mise à jour indiquée ci-dessous et n'est valide que pour une utilisation au Canada. Il est important que vous consultiez toujours les informations actuellement disponibles sur l'URL ci-dessous pour fournir les informations les plus récentes sur le produit au moment de l'utilisation. Des documents supplémentaires tels que les manuels de l'entrepreneur, les bulletins techniques, les dessins détaillés et les recommandations détaillées ainsi que d'autres documents pertinents sont également disponibles sur www.ca.gcpat.com. Les informations trouvées sur d'autres sites Web ne doivent pas être utilisées, car elles peuvent ne pas être à jour ou applicables aux conditions de votre site et nous déclinons toute responsabilité quant à leur contenu. S'il y a des conflits ou si vous avez besoin de plus d'informations, veuillez contacter le service client de GCP.

Last Updated: 2018-12-12

ca.gcpat.com/solutions/products/de-neeef-waterproofing-injection-solutions/de-neeef-rock-tite-b3