

STRUX[®] 90/40 Dosage Rates for Light Use Loading Applications

TB1201

STRUX[®]90/40 Synthetic Macro Fibers are used to replace welded-wire fabric in many slab-on-grade applications, including parking areas, flatwork and flooring. GCP Advanced Technologies (GCP) SDS[™] Software is often used to identify the correct STRUX[®]90/40 fiber dosage rate based on sub base soil conditions, slab thickness, concrete strength and loading conditions. GCP SDS software is a user-friendly, flexible software tool for designing concrete slab-on grade using the latest in synthetic macro fiber technology, STRUX[®]90/40, while determining which design is the most cost-effective for long-term performance under a given slab loading condition. Engineers can view and compare various scenarios of slab thickness vs. fiber dosage rate options, and with local costs, select the most applicable design. However there are several applications that can be designed where one dosage rate would work.

These include residential, light commercial, institutional, retail, office and light vehicle (maximum weight of 10,000 lbs (4,500 kg)) slab on grade. If the design parameters meet the criteria in the following table, the dosage rate of STRUX[®]90/40 fibers shown may be used. For parameters outside those shown in this table, please contact your GCP representative as higher STRUX[®]90/40 dosage rates may be required.

GCP recommends that ACI 302, Guide for Concrete Floor and Slab Construction and ACI 360, Design of Slabs on Grade be consulted when designing and placing concrete slab on grade.

This information is provided as a guide. Final design decisions of the concrete slab are the responsibility of the engineer of record.

UNIT OF MEASURE	SLAB THICKNESS (MINIMUM)	SPECIFIED CONCRETE COMPRESSIVE STRENGTH	MODULUS OF SUBGRADE REACTION(2) (K- VALUE) (MINIMUM)	MAXIMUM LOADING	STRUX [®] 90/40 FIBER DOSAGE RATE
Metric	100 mm	21 to <27.5 Mpa ⁽¹⁾	28 Mpa/m	24 kN/m ²	2.2 kg/m ³
Inch/Pounds	4 in.	3,000 to <4,000 psi ⁽¹⁾	100 lbs/in. ³	500 lbs/ft ²	3.5 lbs/yd ³
Metric	100 mm	27.5 to 40 Mpa	28 Mpa/m	24 kN/m ²	2.5 kg/m ³
Inch/Pounds	4 in.	4,000 to <5,500 psi	100 lbs/in. ³	500 lbs/ft ²	4.0 lbs/yd ³

(1) ACI 302.1R-04, Concrete Floor and Slab Construction, Table 6.1 allows 3,000 psi (21 Mpa) for Floor Classes 1, 2 and 3 (foot traffic), but requires a minimum 3,500 psi (24 Mpa) for Floor Class 4 (foot and light vehicular traffic).

(2) See ACI 360, Design of Slabs on Grade, Section 3.3 – Modulus of Subgrade Reaction, for more information.

ca.gcpat.com | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

STRUX is a registered trademark and SDS is a trademark of GCP Applied Technologies.

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

STRUX is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status. This product is covered by U.S. Patent Nos. 6,569,525; 6,569,526; 6,758,897 and 6,863,969.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140 USA.

In Canada, 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

Ce document est à jour seulement à la date de la dernière mise à jour indiquée ci-dessous et n'est valide que pour une utilisation au Canada. Il est important que vous consultiez toujours les informations actuellement disponibles sur l'URL ci-dessous pour fournir les informations les plus récentes sur le produit au moment de l'utilisation. Des documents supplémentaires tels que les manuels de l'entrepreneur, les bulletins techniques, les dessins détaillés et les recommandations détaillées ainsi que d'autres documents pertinents sont également disponibles sur www.ca.gcpat.com. Les informations trouvées sur d'autres sites Web ne doivent pas être utilisées, car elles peuvent ne pas être à jour ou applicables aux conditions de votre site et nous déclinons toute responsabilité quant à leur contenu. S'il y a des conflits ou si vous avez besoin de plus d'informations, veuillez contacter le service client de GCP.

Last Updated: 2018-12-12

ca.gcpat.com/solutions/products/strux-synthetic-macro-fibers/strux-9040-dosage-rate-s-light-use-loading