

# Daracem<sup>®</sup> 19

Adjuvant réducteur d'eau de grande portée ASTM C494 de type A et F et ASTM C1017 de type I

---

## Product Description

Daracem<sup>®</sup>19 is an aqueous solution of a modified naphthalene sulfonate. Daracem 19 is a superior dispersing admixture having a marked capacity to disperse the cement agglomerates normally found in a cement-water suspension. The capability of Daracem 19, in this respect, exceeds that of normal water-reducing admixtures. It is a low viscosity liquid manufactured for use as received. Daracem 19 contains no added chloride. Daracem 19 is formulated to comply with *Specifications for Chemical Admixtures for Concrete*, ASTM C494 as a Type A and Type F admixture, and ASTM C1017 as a Type I admixture. One gallon of Daracem 19 weighs approximately 10 lbs (1.2 kg/L).

## Uses

Daracem 19 produces concrete with extremely workable characteristics referred to as high slump. Daracem 19 also allows concrete to be produced with very low water/cement ratios at low or normal slumps. Daracem 19 is ideal for use in prestress, precast, bridge deck or any concrete where it is desired to keep the water/cement ratio to a minimum and still achieve the degree of workability necessary to provide easy placement and consolidation. Daracem 19 will also fluidize concrete, making it ideal for tremie concreting or other applications where high slumps are desired.

## Addition Rates

Addition rates of Daracem 19 can vary with type of application, but will normally range from 6 to 20 fl oz/100 lbs (390 to 1300 mL/ 100 kg) of cement. In most instances the addition of 10 to 16 fl oz/ 100 lbs (650 to 1040 mL/100 kg) of cement will be sufficient. At a given water/cement ratio, the slump required for placement can be controlled by varying the addition rate. Should job site conditions require using more than recommended addition rates, please consult your GCP Applied Technologies representative.

## Product Advantages

- Can produce high slump flowable concrete with no loss in strength
- Can produce low water/cement ratio concrete and therefore, high strengths
- Concrete produced with Type I cement may be substituted for normal concrete produced with Type III cement to achieve early strengths
- At high slump, exhibits no significant segregation in comparison to concrete without a superplasticizer at the same slump

## Compatibility with Other Admixtures and Batch Sequencing

Daracem 19 is compatible with most GCP admixtures as long as they are added separately to the concrete mix, usually through the water holding tank discharge line. However, Daracem 19 is not recommended for use in concrete containing polycarboxylate based ADVA<sup>®</sup>superplasticizers or MIRA<sup>®</sup>mid-range water reducers. In general, it is recommended that Daracem 19 be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see GCP Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations.

Pretesting of the concrete mix should be performed before use, and as conditions and materials change in order to assure compatibility, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent (such as Daravair<sup>®</sup>or Darex<sup>®</sup>II AEA) is recommended to provide suitable air void parameters for freeze-thaw resistance. Darex AEA is not recommended. Please consult your GCP Applied Technologies representative for guidance.

## Packaging & Handling

Daracem 19 is available in bulk, delivered by metered tank trucks, in totes and drums Daracem 19 will begin to freeze at approximately 32 °F (0 °C), but will return to full strength after thawing and thorough agitation. In storage, and for proper dispensing, Daracem 19 should be maintained at temperatures above 32 °F (0 °C).

## Dispensing Equipment

A complete line of accurate, automatic dispensing equipment is available.

[ca.gcpat.com](http://ca.gcpat.com) | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

Ce document est à jour seulement à la date de la dernière mise à jour indiquée ci-dessous et n'est valide que pour une utilisation au Canada. Il est important que vous consultiez toujours les informations actuellement disponibles sur l'URL ci-dessous pour fournir les informations les plus récentes sur le produit au moment de l'utilisation. Des documents supplémentaires tels que les manuels de l'entrepreneur, les bulletins techniques, les dessins détaillés et les recommandations détaillées ainsi que d'autres documents pertinents sont également disponibles sur [www.ca.gcpat.com](http://www.ca.gcpat.com). Les informations trouvées sur d'autres sites Web ne doivent pas être utilisées, car elles peuvent ne pas être à jour ou applicables aux conditions de votre site et nous déclinons toute responsabilité quant à leur contenu. S'il y a des conflits ou si vous avez besoin de plus d'informations, veuillez contacter le service client de GCP.

Last Updated: 2018-12-12

[ca.gcpat.com/solutions/products/daracem-19](http://ca.gcpat.com/solutions/products/daracem-19)