

ADVA® 395

High-range water-reducing admixture ASTM C494 Type A and F

Product Description

ADVA®395 admixture is a polycarboxylate based high-range water reducer designed for the production of conventional and Self Consolidating Concrete. It is formulated to provide extended slump life along with excellent workability without segregation.

ADVA®395 is supplied as a ready to use liquid that weighs approximately 8.9 lbs/gal (1.1 kg/L) and does not contain intentionally added chlorides.

Product Advantages

- Excellent moisture and air control
- Extended slump retention up to one hour
- Enhanced concrete cohesiveness with low viscosity for rapid placement
- Superior finish on cast surfaces
- Excellent early and later age compressive strength

Uses

ADVA®395 high-range water reducing admixture is a plant added superplasticizer that is formulated to impart improved workability to concrete over an extended period of time while still achieving high early age compressive strength. It can be used for the production of Self Consolidating Concrete (SCC), and may also be used in conventional concrete production.

ADVA®395 may be used to produce concrete in applications with very low water/cementitious ratios, where concrete stability and improved tolerance to material variability are required, while maintaining high levels of workability over long periods of time.

Addition Rates

ADVA®395 high-range water reducer is an easy to dispense liquid admixture. Dosage rates can be adjusted to meet a wide spectrum of concrete performance requirements. Addition rates can vary from 2 to 10 fl oz/100 lbs (130 to 650 mL/100 kg) with the type of application, but will typically range from 3 to 6 fl oz/100 lbs (200 to 390 mL/100 kg) of cementitious material. Should conditions require using more than the recommended addition rate, please consult your GCP representative.

Mix proportions, cementitious content, aggregate gradations and ambient conditions will affect the product's dosage requirements. If materials or conditions require using more than the recommended addition rates, or when developing mix designs for Self Consolidating Concrete please consult your GCP representative for more information and assistance.



Compatibility with Other Admixtures and Batch Sequencing

ADVA®395 high-range water reducer is compatible with most GCP admixtures as long as they are added separately to the concrete mix. However, ADVA®products are not recommended for use in concrete containing naphthalene based admixtures including DARACEM®19 and DARACEM®100. In general, it is recommended that the product be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see GCP Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations.

Pretesting of the concrete mix should be performed before use and as conditions and materials change in order to assure compatibility with other admixtures, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air entraining agent (such as DARAVAIR® or DAREX® product lines) is recommended to provide suitable air void parameters for freeze thaw resistance. Please consult your GCP representative for guidance.

Packaging & Handling

ADVA®395 high-range water reducer is available in bulk, delivered by metered trucks, in 275 gal (1040 L) totes, and 55 gal (210 L) drums. ADVA®Cast 395 will freeze at approximately 32°F (0°C) but will return to full functionality after thawing and thorough mechanical agitation.

Dispensing Equipment

A complete line of accurate, automatic dispensing equipment is available.

ca.gcpat.com | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

ADVA, DARACEM, DARAVAIR, and DAREX are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 475, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the Canada. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2024-06-21