

ADVA[®] 405

High-range water-reducing admixture ASTM C494 Type A and F and ASTM C1017 Type I

Product Description

ADVA[®]405 is high efficiency polycarboxylate-based superplasticizer intended for the production of Self-Consolidating Concrete (SCC) in ready-mix applications. ADVA[®]405 has been formulated to extend slump-flow life while imparting extreme workability without segregation to concrete.

ADVA[®]405 is supplied as a ready-to-use liquid that weighs approximately 8.65 lbs/gal (1.04 kg/L). ADVA[®]405 does not contain intentionally added chlorides.

Product Advantages

- Enables consistent manufacture of self-consolidating concrete
- Provides extended slump flow retention
- Reduces job site QC support
- Consistent air management

Uses

ADVA[®]405 is recommended for use in the production of Self-Consolidating Concrete and is a component of GCP's Self-Consolidating Concrete System. ADVA[®]405 can also be used as a conventional high-range water reducer.

- Can produce SCC concrete with extremely high levels of workability without segregation.
- Provides superior water tolerance to the concrete making it less susceptible to normal manufacturing moisture fluctuations.
- Extends slump life to enable batch plant adjustments and predictable job site plastic properties.
- Provides superior concrete surface finish characteristics with reduced bugholing.

Compatibility with Other Admixtures and Batch Sequencing

ADVA[®]405 is compatible with most GCP admixtures as long as they are added separately to the concrete mix. However, ADVA[®] products are not recommended for use in concrete containing naphthalene-based admixtures including DARACEM[®]19 and DARACEM[®]100 and melamine-based admixtures including DARACEM[®]65. In general, it is recommended that ADVA[®]405 be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see GCP Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations.

Pretesting of the concrete mix should be performed before use and as conditions and materials change in order to assure compatibility with other admixtures, and to optimize dosage rates, addition times in the batch sequencing, and concrete performance.

For concrete that requires air entrainment, the use of the ASTM C260 air-entraining agent DAREX®II AEA is recommended to provide suitable air void parameters for freeze-thaw resistance. The use of any other AEA should be done in consultation with your GCP Applied Technologies representative for guidance.

Self-Consolidating Concrete

SCC produced with ADVA®405 has unique advantages over conventional flowing concrete.

- Lower SCC viscosity — flow properties of SCC are enhanced, reducing SCC viscosity with no change in stability or segregation resistance.
- Self placement — vibration can be eliminated because SCC is highly flowable and will change shape under its own weight to self level and consolidate within formwork.
- No segregation — SCC is a flowable, yet highly cohesive material that will not segregate. The window of acceptable mix designs to maintain cohesive SCC's is increased. Bleeding is significantly reduced.
- No blocking — SCC can pass freely through narrow openings and congested reinforcement without aggregate “blocking” behind obstructions that stop the flow of concrete.

The production of SCC typically requires both the use of specialty admixtures specifically tailored for SCC such as ADVA®405, as well as mix design adjustments. Therefore, for SCC applications, pre-placement testing is strongly recommended to determine the optimal admixture addition rate and approximate mix design parameters. Factors that influence optimum addition rate include other concrete mix components, aggregate gradations and shapes, form geometry, and reinforcement configurations. Please consult your local GCP Applied Technologies representative for assistance with developing mix designs for Self-Consolidating Concrete.

Addition Rates

ADVA®405 is an easy to dispense liquid admixture. Dosage rates can be adjusted to meet a wide spectrum of concrete performance requirements. Addition rates for ADVA®405 can vary with the type of application, but will normally range from 12 to 18 fl oz/100 lbs (785 to 1175 mL/100 kg) of cement. Should conditions require using more than the recommended addition rate, please consult your GCP Applied Technologies representative.

Packaging & Handling

ADVA®405 is available in bulk, delivered by metered trucks, in totes and drums. ADVA®405 will freeze at approximately 32 °F (0 °C) but will return to full functionality after thawing and thorough mechanical agitation.

Dispensing Equipment

A complete line of accurate, automatic dispensing equipment is available.

ca.gcpat.com | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

ADVA, DARACEM, and DAREX are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 450, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the Canada. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-04-27

ca.gcpat.com/solutions/products/adva-high-range-water-reducers/adva-405