

ADVA® FLEX

High-range water-reducing admixture ASTM C494 Type A and F, and ASTM C1017 Type I

Product Description

ADVA [®]FLEX is a revolutionary advancement in time activated polycarboxylate-based high-range water reducer technology. This patent pending, workability (slump and flow) enhancing admixture may be used as an every day high-range water reducer or, at higher dosage rates, it will significantly increase the length of slump or flow retention. ADVA [®]FLEX is formulated to comply with the requirements of ASTM C494 Type A and F admixture and ASTM C1017 Type I plasticizing. ADVA [®]FLEX does not contain chloride as a functional ingredient. ADVA [®]FLEX is manufactured under closely controlled conditions and formulated for use as received. One gallon weighs approximately 8.9 lbs (1.1 kg/L).

Product Advantages

- Flexibility to use as a traditional high-range water reducer or a workability retaining high-range water reducer
- Opportunity to better control operational costs by adjusting the slump life retention on an "as needed" basis during the initial dosage adjustment
- Concrete finishes easily without stickiness, spotty setting or tearing
- Added at the batch plant for rapid batching
- Eliminates the need for re-tempering at the job site

Uses

ADVA [®]FLEX is specifically intended for use where extended workability with minimal time of setting extension is desired without compromising plastic or hardened concrete properties. ADVA [®]FLEX produces concrete with high slump properties and allows concrete to be produced with very low water/cement ratios while providing the degree of workability necessary to provide easy placement and consolidation.

Conventional high-range water reducers may not provide sufficient slump life for applications with unpredictable or long transportation and placement times. As a result, concrete may need to be retempered at a job site to achieve desired workability.

Addition Rates

Addition rates of ADVA®FLEX can vary with the type of application, but may range from 4 to 14 oz/100 lbs (260 to 910 mL/100 kg) of cementitious as a conventional high-range water reducer with typical addition rates of 8 to 12 oz/100 lbs (520 to 780 mL/100 kg) as an extended slump life high-range water reducer. At higher dosage rates, some water may have to be removed from the mix to maintain plastic concrete cohesion. For concrete performance information using ADVA®FLEX, please see GCP Technical Bulletin TB-0607, ADVA®FLEX. GCP strongly recommends pretrial testing the concrete with ADVA®FLEX before production use to optimize dosage rates due to concrete materials, ambient conditions and project requirements that change over time. Please consult your GCP Applied Technologies representative for more information and assistance. Distribute with permission only.



Compatibility with Other Admixtures and Batch Sequencing

ADVA®FLEX is compatible with most GCP admixtures as long as they are added separately to the concrete mix. However, ADVA®products are not recommended for use in concrete containing naphthalene-based admixtures including DARACEM®19 and DARACEM®100, and melamine-based admixtures including DARACEM®65. In general, it is recommended that ADVA®FLEX be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see GCP Technical Bulletin TB-0110, Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations for further recommendations.

Pretesting of the concrete mix should be performed before use and as conditions and materials change in order to assure compatibility with other admixtures, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent (such as DARAVAIR® or DAREX® product lines) is recommended to provide suitable air void parameters for freeze-thaw resistance. Please consult your GCP Applied Technologies representative for guidance.

Packaging & Handling

ADVA®FLEX is available in bulk delivered by metered trucks, in 275 gal (1040 L) disposable totes and in 55 gal (208 L) drums.

ADVA [®]FLEX should be stored at temperatures above $32^{\circ}F$ ($0^{\circ}C$) and below $120^{\circ}F$ ($50^{\circ}C$) for proper dispensing and use. It will begin to freeze at $32^{\circ}F$ ($0^{\circ}C$), but will return to full strength after thawing and thorough agitation.

Dispensing Equipment

A complete line of accurate, automatic dispensing equipment is available.

ca.gcpat.com | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

ADVA, DARACEM, DAREX, and DARAVAIR are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 475, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the Canada. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2024-06-21