

DARAGRIND[®] Mineral Grinding Aid

Mineral Grinding Aid

Product Description

DARAGRIND[®] is one of the largest product developments by GCP Applied Technologies in the field of Grinding Additives for minerals, cement raw materials, coal, pure calcium carbonate, limestone, silica and quicklime.

Addition Rates

The dosage rate of DARAGRIND[®]can vary from 0.005% to 0.1% by weight. The optimum dosage rate will depend on the fineness and the re-agglomeration characteristics of each material.

Dosing Equipment

DARAGRIND[®] should be accurately dispensed through a calibrated dosing system, suitable for mill and production rate.

GCP can advise on suitable equipment for installation, covering manual, semi-automatic and computerized systems.

Handling

DARAGRIND[®]may be sprayed as received into the mill or added onto conveyor belt. DARAGRIND[®]can be diluted with up to 8 parts of water to ensure greater proportioning accuracy and better distribution.

Technical Service

To assist you in obtaining optimum performance from your GCP Cement Additive, we offer advice and assistance by trained personnel, experienced in additive technology, and the facilities of our fully equipped laboratories.

Product Advantages

- Increased mill output at same fineness
- Increased fineness for same energy input
- Reduced grinding costs
- Increased powder flowability

MATERIAL GROUND	DOSAGE (GRAMS PER TONNE)
Cement Raw Materials, Coal	200-800
Silica	500-1000
Calcium Carbonate/Limestone	400-1000



50-400

Safety Information

DARAGRIND[®]products are non flammable.

A SDS (Safety Data Sheet) is available upon request.

Packaging

Lime

DARAGRIND[®] products can be supplied in 205 litre drums, 1000 litre bulk boxes and in bulk tankers.

Storage

The shelf life of DARAGRIND[®] products is a minimum of 12 months in original containers.

ca.gcpat.com | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Daragrind is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 475, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the Canada. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.