

DARASET[®] 442

Set-accelerating admixture ASTM C494 Type C

Product Description

DARASET[®]442 is a non-corrosive, non-chloride admixture for concrete. It accelerates cement hydration resulting in shortened setting times and increased early compressive and flexural strengths. DARASET[®]442 does not contain calcium chloride and is non-corrosive to reinforcing steel, to metal decks and to metal components of admixture storage and dispensing systems. It is formulated to comply with ASTM C494 Type C, and can be used at any dosage to comply with ACI 318 guidelines for chloride content of concrete. DARASET[®]442 weighs approximately 11.5 lbs/gal (1.38 kg/L).

Uses

DARASET[®]442 may be used wherever it is desirable to reduce the setting time of concrete and/or to increase its early compressive and flexural strengths. For mixes designed with pozzolans, such as fly ash or slag, DARASET[®]442 can help offset the retarding effects of these materials, especially in cooler temperatures.

In cold weather, DARASET[®]442 may be used to reduce the time that it takes the concrete to set, prior to finishing. Typical results show that when concrete containing DARASET[®]442 is poured at 50 °F (10 °C), the concrete will set up to 2 hours faster than the reference concrete.

When used in the manufacture of precast concrete, DARASET[®]442 speeds the concrete's strength development allowing for earlier form removals and more efficient production. DARASET[®]442 can also be used in masonry mortar to obtain higher early strengths and accelerated setting time effects.

Product Advantages

- Accelerates setting time
- Increases early compressive and flexural strengths
- Offsets the retarding effects of pozzolans such as slag or fly ash
- Non-corrosive

Special Feature

DARASET[®]442 non-corrosive, non-chloride set accelerator provides setting time results and early strength development similar to that provided by calcium chloride, but without the potential corrosive effects. DARASET[®]442 can, therefore, at recommended dosage rates, safely be used where the potential corrosion of embedded or stressed steel must be avoided. It can also be used in concrete that is to be placed on steel clad or zinc coated steel decks where corrosion must be similarly avoided.

Compatibility with Other Admixtures and Batch Sequencing

DARASET®442 is compatible with most GCP admixtures as long as they are added separately to the concrete mix, usually through the water holding tank discharge line. In general, it is recommended that DARASET®442 be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see GCP Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations.

Pretesting of the concrete mix should be performed before use, as conditions and materials change in order to assure compatibility, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent (such as DARAVAIR® or DAREX® product lines) is recommended to provide suitable air void parameters for freeze-thaw resistance. Please consult your GCP Applied Technologies representative for guidance.

Mix Adjustment

Since DARASET®442 may be used at high dosages, the concrete producer should account for the water contained in the product. Each gallon of DARASET®442 added to a concrete mix will contribute 6.3 lbs (0.76 kg/L) of water to that mix.

Packaging & Handling

DARASET®442 is currently available in bulk quantities by GCP metered systems, or in totes and drums.

DARASET®442 freezes at approximately -10°F (-23°C), but its set acceleration, strength gain and non-corrosive properties are completely restored by thawing and thorough agitation.

Performance

In concrete mixtures, DARASET®442 accelerates the chemical reaction between Portland cement and water. It speeds up the formation of gel—the binder that bonds concrete aggregates together. Accelerated gel formation in turn shortens the setting time of concrete, compensates for the set-slowing effects of cooler weather, and contributes to the development of higher early strengths.

Addition Rates

The amount of DARASET®442 used will depend on specific job conditions, on local materials and on the degree of set acceleration and early strength development required. Typical addition levels range from 10 to 60 fl oz/100 lbs (650 to 3910 mL/100 kg) of cement. Higher dosage rates may be used for select applications after consulting with your local GCP Applied Technologies sales representative.

Dispensing Equipment

A complete line of accurate dispensers is available. While DARASET®442 may be added to the mix on the sand or in the water, for greatest effectiveness, we recommend DARASET®442 be added at the end of the batch cycle.

Similar to all concrete admixtures, DARASET®442 should not come into contact with other admixtures prior to entering the concrete.

Specifications

The set-accelerating admixture shall be DARASET®442, non-corrosive, non-chloride set accelerator, as manufactured by GCP Construction Products. The admixture shall be used in strict accordance with the manufacturers' recommendations. The admixture shall comply with ASTM Designation: C494 Type C and will not contain purposely added chlorides or contribute to steel corrosion. Certification of compliance will be made available upon request.

Concrete shall be proportioned in accordance with *Recommended Practice for Selecting Proportions for Normal Weight Concrete*, ACI 211.1 or *Recommended Practice for Selecting Proportions for Structural Lightweight Concrete*, ACI 211.2, or in accordance with ACI 318.

ca.gcpat.com | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Daraset, Daravair and Darex are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 450, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the Canada. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2023-06-29

ca.gcpat.com/solutions/products/daraset-442