

PREPRUFE[®] Grout EG 75

Three part epoxy grout for waterproofing of pile heads

Product Description

PREPRUFE[®]Grout EG 75 is a high performance, solvent free, impermeable epoxy grout for maintaining the continuity of PREPRUFE[®]waterproofing systems at pile heads and similar structural penetrations. The product comprises of a base epoxy resin, an epoxy hardener and graded mineral aggregates. The three components are supplied pre-measured for easy onsite mixing at the correct ratio.

Uses

- Waterproofing of pile heads and pile caps
- Waterproofing of structural penetrations through PREPRUFE[®] waterproofing systems
- Application thickness range 1/2" (13mm) - 3" (75 mm)

System Components

To achieve continuity of PREPRUFE[®]waterproofing systems at pile heads and similar structural penetrations, the following system components are needed.

- BITUTHENE[®] Liquid Membrane – high performance, liquid membrane
- PREPRUFE[®] 300R or 300R Plus sheet membrane
- PREPRUFE[®] Tape for sealing of laps in PREPRUFE[®] sheet membranes

Consult with your GCP Applied Technologies technical representative for guidance on proper detailing.

Product Advantages

- Compatible with all products in the PREPRUFE[®] sheet waterproofing system
- Impermeable
- High bond to substrate
- Rapid strength gain
- High compressive, flexural and tensile strengths
- Fluid consistency
- Solvent free
- No segregation or shrinkage
- Highly resistant to acids, alkalies, common salts and sulphates
- Easy mixing and placing

Applications

Surface Preparation:

All surfaces to be in contact with PREPRUFE® Grout EG75 shall be free of oil, grease, laitance and other contaminants. Concrete must be clean, sound and roughened to ensure a good bond. For optimum adhesion, concrete should be visibly free of surface moisture. Remove rust from any reinforcement that will be in contact with the epoxy grout.

Formwork:

Formwork may be utilized for more accurate placement and is required to be constructed at vertical surfaces to obtain minimum 1/2-inch thickness. Formwork shall be constructed of a rigid, non-absorbent material, and caulked liquid tight. All removable formwork should be coated with polyethylene film or wax release agent, before the grout is placed.

Contact your GCP Applied Technologies technical service representative for further information

Mixing and Placing:

For optimum performance, all components should be conditioned to between 70°F and 80°F (21°C and 27°C) prior to use. Using a clean metal pail, pour component A into the pail. Add component B and mix using a clean paddle mixer and slow speed drill (max 400 rpm) for two minutes. Heat is generated when components A and B are mixed and temperatures will increase with time. Therefore, the full contents of component C is required to be slowly added immediately after mixing components A and B. Mix continuously and scrape unmixed material from the side and bottom of pail with a trowel. Mix for a minimum of three minutes or until a flowable homogenous consistency is achieved.

Working time is approximately 30 minutes when temperatures are at 70° F (21° C). Pour the grout from the pail into the forms continuously. If more grout is required, mix the next unit while the first is being poured to enable continuous placement. Finish with a trowel where necessary.

Grout temperature shall be maintained above 50° F until grout reaches the required strength.

Cleaning:

All tools and equipment may be cleaned with a water and strong detergent solution or suitable solvent before material hardens. Sand may be used as an abrasive.

Re-profiling Grout:

Where the use of cementitious re-profiling grout is necessary, use PREPRUFE® Grout CEM 100 or other equivalent repair or re-profiling mortar. Do not use site batched sand/cement mortars.

Health and Safety

Users must read and understand the product label and Safety Data Sheets (SDSs) for each system component before use. All users should acquaint themselves with this information prior to working with the material. Carefully read detailed precaution statements on the product labels and SDSs before use. The most current SDSs can be obtained from the GCP web site at gcpat.com or by contacting GCP toll free at 1-866-333-3SBM (3726).

Supply and Storage

PREPRUFE® Grout EG75 is a three-component system consisting of resin, hardener and aggregate packaged separately in a pail, and is available in a unit yielding approximately 0.50 cubic feet (14.2 liters) of hardened material.

COMPONENT	TYPE	PACKAGING	UNIT SIZE	THEORETICAL COVERAGE AT ½ INCH THICKNESS
Total Mixed			0.50 cu.ft	12 ft ²
A	Epoxy base resin	Metal can	9.5 lbs.	
B	Epoxy hardener	Metal can	1.5 lbs.	
C	Filler	Heavy duty paper bag	50 lbs.	

Store unopened in original packaging in cool, dry conditions out of direct sunlight and remote from direct heat sources. Shelf life in these conditions is 12 months from date of manufacture.

Physical Properties

PREPRUFE® GROUT EG-75	TYPICAL VALUE	TEST METHOD
Thickness range	1/2 - 3 in	
Flow at 73°F	9.8 in	ASTM C 230
Flow at 113°F	11 in	ASTM C 230
Pot Life at 73°F	45 mins	ASTM C 308 (modified)
Pot Life at 113°F	30 mins	ASTM C 308 (modified)
Peel Adhesion to PREPRUFE® membrane	> 4 pli	ASTM D 3330
Compressive strength 7 day at 73°F	11,000 psi	ASTM C 579
Flexural Strength 7 day at 73°F	3800 psi	ASTM C 580
Tensile strength 7 day at 73°F	2200 psi	ASTM C 307
Bond strength to concrete 7 day at 73°F	365 psi	ASTM D 4541
Fresh Mixed Density	4.6 lbs/gal	ASTM C 905-79
Water penetration	None	BS 12390-8
Rapid Chloride Permeability	None	ASTM C 1202

Note: All test results shown in this data sheet are determined under laboratory conditions, using product samples taken from inventory in original packaging, without alteration or modification.

gcpat.com | North America customer service: 1-866-333-3726

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

PREPRUFE is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2021 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 450, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the Canada. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-04-27

ca.gcpat.com/solutions/products/preprufe-comprehensive-waterproofing-system/preprufe-grout-eg-75