

QUANTEC[®] NC-525P

Plasticizing, Non-Chloride Set Accelerator

Product Description

QUANTEC[®]NC-525P is a non-chloride, non-corrosive plasticizing admixture specially formulated for use in the manufacture of machined concrete products where the process requires zero or very low slump concrete and accelerated early strengths.

QUANTEC[®]NC-525P is supplied as a chemically formulated ready-to-use liquid. Its low viscosity, approximating that of water, ensures rapid, accurate dispensing. QUANTEC[®]NC-525P does not contain calcium chloride or contribute to efflorescence. Companion products to QUANTEC[®]NC-525P are QUANTEC[®]PL-466 for a smoother, denser surface with a swipe, and QUANTEC[®]PL-477R for normal textured, low slump concrete block.

Product Advantages

- Non-chloride/non-corrosive
- Accelerated strengths
- Reduction or elimination of steam curing
- Reduction in fuel costs
- Increased throughput
- Better compaction
- Increased plasticity
- Reduced cracking and crazing
- Sharper corners and edges
- Improved texture
- Fewer culls
- Cost effective

Product Uses

QUANTEC[®]NC-525P may be used in all zero or low slump concrete to increase workability while retaining cohesiveness, and providing more rapid hydration of the cement. In addition, QUANTEC[®]NC-525P gives the acceleration necessary to provide high early strength while reducing or eliminating the requirement for steam curing. This benefit can also allow for replacement of Type I Cement for Type III Cement. QUANTEC[®]NC-525P is intended for use in normal weight and lightweight concrete block mixes and may be beneficially used in concrete pipe, concrete tile and concrete brick.

The mixes designed for these products are characteristically dry, containing minimal water. Additional water would be desirable to allow for complete hydration of the cement and improve mix cohesiveness. However, an increase in water content is impractical from a production standpoint. A very low or zero slump is necessary for dimensional stability of the units upon removal from the mold.

The use of QUANTEC®NC-525P will compensate for the water deficiency in such mixes. QUANTEC®NC-525P is both a plasticizing agent as well as an accelerating agent. By dispersing the cement and aggregate fines, it improves the workability of the mix. Dispersion of the cement results in more complete hydration. This coupled with the acceleration produced by QUANTEC®NC-525P provides greater early strength for any given cement content. Addition of QUANTEC®NC-525P can increase the early compressive strength of the block at the same cement content.

The increased workability provided by QUANTEC®NC-525P allows for better compaction of the block with less cracking and crazing, sharper corners and edges, resulting in fewer culls. Production can be increased, absorption reduced and appearance and texture greatly improved.

Application Information

Addition Rates

QUANTEC®NC-525P is used at the rate of 390-780 mL/100 kg (6-12 fl oz/100 lbs) of cementitious materials in the mix.

Dispensing Equipment

A complete line of admixture dispensing equipment is available.

Packaging

QUANTEC®NC-525P is available in drums and returnable totes.

Health & Safety

All precautions defined on the SDS (Safety Data Sheet) for QUANTEC®NC-525P must be followed.

Storage

QUANTEC®NC-525P will begin to freeze at approximately -4°C (25°F), but will return to full strength after thawing and thorough mechanical agitation.

ca.gcpat.com | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

QUANTEC is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 475, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the Canada. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2024-06-21

ca.gcpat.com/solutions/products/masonry-hardscape-solutions/quantec-nc-525p