

QUANTEC[®] PL-495R

Concentrated plasticizer

Product Description

QUANTEC[®]PL-495R admixture is a concentrated plasticizer specially formulated for use in concrete block, concrete pipe and other zero or low slump concrete products where a normal textured surface is desired.

QUANTEC[®]PL-495R admixture is supplied as a liquid concentrate, but it is intended to be used in a diluted form.

Product Advantages

- Normal texture
- Increased throughput
- Sharper corners and edges
- Fewer culls
- Cost effective
- Better compaction

Product Uses

QUANTEC[®]PL-495R admixture may be used in all zero or low slump concrete to increase workability while retaining cohesiveness and to provide for more complete hydration of the cement. QUANTEC[®]PL-495R admixture is a plasticizer which improves the dispersion of the cement throughout the mix as well as improving the workability of the mix which can improve machine efficiency.

The increased workability achieved with QUANTEC[®]PL-495R admixture allows for better compaction of the block with less cracking and sharper corners and edges, resulting in fewer culls. Production can be improved while maintaining a smoother, denser surface with a normal texture.

Packaging

QUANTEC[®]PL-495R admixture is available in drums and returnable totes.

Application Information

Addition Rates

QUANTEC[®]PL-495R admixture is supplied as a concentrate, but it is recommended that it be diluted prior to use. The recommended dilution rate is one part QUANTEC[®]PL-495R admixture to ten parts water.

Add 30 gallons (114 L) of water to a 55 gal (208 L) drum. Then add 5 gallons (19 L) of QUANTEC®PL-495R. While mixing, add the remainder of the water to the drum and mix until homogeneous. Use this solution at a dosage rate of 3-7 fl oz/cwt (195-455 mL /100 kg) of cementitious material, including pozzolans. If desired, QUANTEC®PL-495R admixture may also be used in concentrated form. As a concentrate, QUANTEC®PL-495R admixture is used at the rate of 0.3-0.7 fl oz/cwt (20-45 mL/100 kg) of cementitious material, including pozzolans.

Health & Safety

All precautions defined on the SDS (Safety Data Sheet) for QUANTEC®PL-495R admixture must be followed.

Storage

QUANTEC®PL-495R admixture will begin to freeze at approximately 32 °F (0 °C) but will return to full effectiveness after thawing and mechanical agitation.

ca.gcpat.com | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

QUANTEC is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 450, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the Canada. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-11-25

ca.gcpat.com/solutions/products/masonry-hardscape-solutions/quantec-pl-495r