

# QUANTEC<sup>®</sup> XL-524P

Set accelerating plasticizer

---

## Product Description

QUANTEC<sup>®</sup>XL-524P admixture is a non-chloride based plasticizing set accelerator for machine produced concrete products where the process requires zero or very low slump concrete.

## Product Advantages

- Hastens hydration process
- Increased throughput
- Better compaction
- Increased plasticity
- Reduced cracking and crazing
- Sharper corners and edges
- Fewer culls

## Product Uses

QUANTEC<sup>®</sup>XL-524P admixture may be used in all zero or low slump concrete to increase workability while retaining cohesiveness and providing more rapid hydration of the cement. In addition, the admixture gives the acceleration necessary to provide early strength while reducing or eliminating the requirement for steam curing. This benefit can also allow for replacement of Type III Cement with Type I Cement.

QUANTEC<sup>®</sup>XL-524P admixture is intended for use in concrete block mixes and may be beneficially used in concrete pavers and segmental retaining wall units. QUANTEC<sup>®</sup>XL-524P admixture is both a dispersing agent as well as an accelerating admixture. By dispersing the cement and aggregate fines, it improves the workability of the mix. Dispersion of the cement results in more complete hydration. This, coupled with the acceleration produced by QUANTEC<sup>®</sup>XL-524P admixture, provide greater early strength for any given cement content.

The increased workability provided by the admixture allows for better compaction with less cracking and crazing, sharper corners and edges, resulting in fewer culls. Production can be increased, absorption reduced and appearance and texture greatly improved.

## Application Information

### Addition Rates

QUANTEC<sup>®</sup>XL-524P admixture is used at a rate of 6-10 oz/cwt (390-650 mL/100 kg) of cementitious materials, including pozzolans. The addition rate is dependent upon the specific set of materials and the desired end properties.

## Packaging

QUANTEC®XL-524P admixture is available in drums and returnable totes.

## Health & Safety

All precautions defined on the SDS (Safety Data Sheet) for QUANTEC®XL-524P admixture must be followed.

## Storage

QUANTEC®XL-524P admixture will begin to freeze at approximately 32 °F (0 °C), but will return to full strength after thawing and thorough mechanical agitation.

[ca.gcpat.com](http://ca.gcpat.com) | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

QUANTEC is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 450, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the Canada. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com](http://www.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-11-25

[ca.gcpat.com/solutions/products/masonry-hardscape-solutions/quantec-xl-524p](http://ca.gcpat.com/solutions/products/masonry-hardscape-solutions/quantec-xl-524p)