

TL-0007 – Waterproofing Concrete Block Walls Technical Letter

Below grade waterproofing CMU walls is critical since most CMU is porous and therefore susceptible to moisture and water infiltration. Standard application procedures for Bituthene[®] and Procor[®] should be followed and particular attention should be placed on the following:

- The CMU surface should be smooth and free from projections. Trowel mortar joints full and flush to the face of the CMU. Fill all voids and holes. If these conditions are not met, cover CMU with a parge coat (typically one part cement to three parts sand) finished to a smooth steel trowel surface.
- Tightly grout around all penetrations prior to installing the waterproofing.
- The CMU must be thoroughly dry before installing the waterproofing. Because of the porosity of the CMU, water can wick through much of the wall. Moisture in the block wall is usually detectable due to a discoloration of the CMU. If the CMU cores are grouted, allow 3 days of drying prior to installing the waterproofing. Use Bituthene[®] B2 LVC if the block is damp for Bituthene[®] application. Procor[®] is damp and green concrete tolerant and does not require a primer.
- Immediately roll Bituthene[®] completely and firmly with a hand roller upon application. Press the top termination of membrane firmly to the wall with a blunt tool such as the handle of a hammer or secure the membrane into a reglet.
- Use a termination bar to terminate Bituthene[®] on CMU walls. Use a 1/8 in. x 1 in. x 10 ft (3 mm x 25 mm x 3.05 m) max aluminum bar. Fasten 12 in. (305 mm) O.C. or as necessary to ensure continuous compression and 1 in. (25 mm) in from end of all sections. Separate adjoining bars by 1 4 in. (6 mm). Seal top of bar and penetration heads with Bituthene[®] Liquid Membrane.
- For Procor[®] applications on highly porous CMU, a scratch coat of Procor[®] (15–30 mils) can be applied prior to the standard Procor[®] application.
- When necessary, provide temporary weather protection, such as plastic or tarpaulin, over the top of the wall to prevent precipitation from accumulating in the core of the CMU, or against the interior face during concrete floor pours.

North America customer service: 1-877-4AD-MIX (1-877-423-6491)

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 475, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the Canada. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2024-06-21

ca.gcpat.com/solutions/products/bituthene-post-applied-waterproofing/tl-0007-waterproofing-concrete-block-walls