

V-MAR[®] F100

Concrete rheology-modifying admixture ASTM C494 Type S

Product Description

V-MAR[®]F100 is a high efficiency, rheology-modifying liquid admixture. The use of V-MAR[®]F100 admixture imparts lubricity to the concrete resulting in increased productivity and concrete with improved surface texture.

V-MAR[®]F100 admixture is supplied as a ready to use liquid that weighs approximately 8.5 lbs/gal (1.02 kg/L). V-MAR[®]F100 admixture does not contain intentionally added chlorides.

Product Advantages

Concrete produced with V-MAR[®]F100 offers the following advantages:

- Increased productivity through higher throughput
- Concrete moves easier and faster through machinery
- Improved paste creaminess and enhanced finishability
- Concrete consolidates with reduced vibration
- Provides superior water tolerance to the concrete making it less susceptible to normal manufacturing moisture fluctuations
- Facilitates the use of angular aggregates and/or manufactured sands in concrete

Uses

V-MAR[®]F100 is a multi-purpose admixture that reduces friction within the concrete mixture, resulting in a highly workable mixture.

V-MAR[®]F100 can be used for conventional slump concrete and SCC mixtures. It is particularly effective in zero slump and low slump applications such as concrete pipe, concrete extrusion, concrete paving, slip formed concrete and roller-compacted concrete.

Addition Rates

V-MAR[®]F100 is an easy to dispense liquid admixture. Dosage rates can be adjusted to meet a wide spectrum of concrete performance requirements. Addition rates for V-MAR[®]F100 can vary with the type of application, but will normally range from 3–12 fl oz/100 lbs (195–780 mL/100 kg). In most cases, the addition of 5–8 fl oz/ 100 lbs (325–520 mL/ 100 kg) of cementitious material will be sufficient. Please consult your GCP Applied Technologies representative for assistance with developing mix designs.

Packaging & Handling

V-MAR[®]F100 is available in bulk, in totes, and drums.

V-MAR[®]F100 will freeze at approximately 28°F (-2°C) but will return to full functionality after thawing and thorough mechanical agitation.

Dispensing Equipment

A complete line of accurate, automatic dispensing equipment is available.

Compatibility with Other Admixtures and Batch Sequencing

V-MAR[®]F100 is compatible with most GCP admixtures as long as they are added separately to the concrete mix. V-MAR[®]F100 should be added to the concrete mix as early as possible in the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see GCP Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations.

Pretesting of the concrete mix should be performed prior to use and as job conditions and materials change, in order to ensure compatibility with other admixtures, and to optimize dosage rates and addition times in the batch sequencing, in order to optimize concrete performance.

For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent is recommended to provide suitable air void parameters for freeze-thaw resistance. Please consult your GCP Applied Technologies representative for guidance.

ca.gcpat.com | North America customer service: 1-877-4AD-MIX (1-877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

V-MAR is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 450, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the Canada. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2023-06-29

ca.gcpat.com/solutions/products/v-mar-admixtures/v-mar-f100